

Electrical Engineering

Analog Electronics

Comprehensive Theory

with Solved Examples and Practice Questions



MADE EASY
Publications



MADE EASY Publications Pvt. Ltd.

Corporate Office: 44-A/4, Kalu Sarai (Near Hauz Khas Metro Station), New Delhi-110016

E-mail: infomep@madeeasy.in

Contact: 011-45124660, 8860378007

Visit us at: www.madeeasypublications.org

Analog Electronics

© Copyright by MADE EASY Publications Pvt. Ltd.

All rights are reserved. No part of this publication may be reproduced, stored in or introduced into a retrieval system, or transmitted in any form or by any means (electronic, mechanical, photo-copying, recording or otherwise), without the prior written permission of the above mentioned publisher of this book.

First Edition : 2015

Second Edition : 2016

Third Edition : 2017

Fourth Edition : 2018

Fifth Edition : 2019

Sixth Edition : 2020

Seventh Edition : 2021

Eighth Edition : 2022

Contents

Analog Electronics

Chapter 1

Semiconductor Physics 1

1.1 Conductor, Semiconductor and Insulator.....	1
1.2 The Mass-action Law.....	5
1.3 Charge Neutrality Equation.....	7
1.4 Drift Current.....	8
1.5 Current Density (J).....	8
1.6 Diffusion Current.....	11
1.7 Einstein Relation.....	13
1.8 Potential Variation in a Open Circuit Semiconductor Bar.....	13
Student Assignments.....	14

Chapter 2

Semiconductor Diode 16

2.1 Representation for n-type and p-type Semiconductors...	16
2.2 p-n Junction Theory.....	16
2.3 Forward-bias Condition ($V_D > 0\text{ V}$).....	18
2.4 Reverse-bias condition ($V_D < 0\text{ V}$).....	19
2.5 Expression for Diode Current.....	20
2.6 The Ideal Diode.....	22
2.7 The Contact Potential.....	23
2.8 Step Graded Diode or Abrupt pn-junction Diode.....	24
2.9 Space-charge, or Transition, Capacitance C_T	25
2.10 Diffusion Capacitance or Storage Capacitance.....	28
2.11 Phenomenon of Breakdown.....	28
2.12 Zener Diodes.....	29
2.13 Junction Diode Switching Time.....	30
Student Assignments.....	32

Chapter 3

Field Effect Transistors 34

3.1 FET Vs BJT.....	34
3.2 Construction of JFETs.....	35
3.3 MOSFETs.....	43
3.4 Enhancement Type MOSFET.....	46

3.5 The p-channel MOSFET.....	50
Student Assignments.....	54

Chapter 4

Diode Circuits 56

4.1 Introduction.....	56
4.2 Diode Circuits : DC Analysis and Models.....	56
4.3 Diode Logic Gates.....	63
4.4 Diode : The Small Signal Model.....	65
4.5 DC Power Supply.....	67
4.6 Rectifier.....	67
4.7 Half-wave Rectifier.....	68
4.8 Centre-Tapped Full-wave Rectifier.....	77
4.9 Bridge Rectifier.....	85
4.10 Comparison of Rectifier Circuits with Resistive Load.....	88
4.11 Filter.....	88
4.12 Inductor Filter.....	88
4.13 Capacitor Filter.....	91
4.14 CLC Filter (P-Section Filter).....	95
4.15 Voltage Regulators.....	96
4.16 Zener Diode Shunt Regulator.....	98
4.17 Op-amp Controlled Series Regulator.....	99
4.18 Transistorized Series Regulator.....	100
4.19 Wave Shaping.....	103
4.20 Clipper.....	103
4.21 Linear Wave Shaping.....	110
4.22 Clamper.....	117
4.23 Voltage Multiplier.....	120
Student Assignments.....	122

Chapter 5

BJT-Characteristics and Biasing 126

5.1 Introduction.....	126
5.2 Transistors Current Components.....	126
5.3 Early Effect.....	130

5.4	BJT Configuration.....	131
5.5	The Common Base Configuration.....	132
5.6	The Common-Emitter Configuration.....	134
5.7	The Common-Collector Configuration	137
	<i>Student Assignments</i>	137

Chapter 6

Transistor Biasing and Thermal Stabilization 140

6.1	Introduction.....	140
6.2	The Operating Point.....	140
6.3	Instability in Collector Current	142
6.4	BJT Biasing	145
6.5	Fixed Bias Circuit.....	145
6.6	Collector to Base Bias Circuit.....	147
6.7	Self-Bias, Emitter Bias, or Voltage-Divider Bias	148
6.8	Bias Compensation.....	151
6.9	Thermal Runaway	153
6.10	BJT Biasing in Integrated Circuits (ICs)	156
6.11	Constant Current Source (Current Mirror).....	156
6.12	Widlar Current Source	158
6.13	Current Repeaters	159
6.14	Wilson Current Source.....	160
	<i>Student Assignments</i>	162

Chapter 7

BJT as an Amplifier 165

7.1	Introduction.....	165
7.2	Graphical Analysis of BJT Amplifier	166
7.3	Transistor Hybrid Model	167
7.4	Analysis of Transistor Amplifier Circuit Using h-Parameters.....	168
7.5	Small Signal Hybrid-II Equivalent Circuit of BJT.....	174
7.6	Hybrid-II-Equivalent Circuit, by Considering Early Effect	175
7.7	Basic Transistor Amplifier Configurations	177
7.8	Common-Emitter Amplifiers.....	177
7.9	Common-Collector (Emitter-Follower) Amplifier.....	183
7.10	Common-Base Amplifier	186
7.11	Multistage Amplifiers.....	189
	<i>Student Assignments</i>	191

Chapter 8

Basic FET Amplifiers 194

8.1	Introduction	194
8.2	The Common-Source Amplifier	194
8.3	Common-Drain (Source Follower) Amplifier.....	199
8.4	The Common-Gate Configuration	201
	<i>Student Assignments</i>	206

Chapter 9

Frequency Response 208

9.1	Introduction	208
9.2	Amplifier Frequency Response	208
9.3	Miller's Theorem	215
9.4	Frequency Response : BJT	216
9.5	High Frequency Response of Common-Emitter and Common-Source Circuits	221
9.6	High Frequency Response of Common-Base and Common-Gate Circuits.....	223
9.7	High Frequency Response of Emitter and Source Follower Circuits	225
	<i>Student Assignments</i>	228

Chapter 10

Differential Amplifiers 230

10.1	Introduction	230
10.2	The Differential Amplifier	230
10.3	Basic BJT Differential Amplifier	231
10.4	FET Differential Amplifiers	237
10.5	Constant Current-Bias	238
10.6	Level Translator	240
	<i>Student Assignments</i>	242

Chapter 11

Feedback Amplifiers..... 243

11.1	Introduction	243
11.2	Basic Feedback Concepts.....	243
11.3	General Block Diagram of Feedback Amplifier.....	247
11.4	Four Basic Feedback Topologies.....	250
11.5	Series-Shunt Configuration	251

11.6 Shunt-Series Configuration	253
11.7 Series-Series Configuration	255
11.8 Shunt-Shunt Configuration	256
11.9 Summary of Results.....	256
<i>Student Assignments</i>	258

Chapter 12

Operational Amplifier.....261

12.1 Introduction	261
12.2 Block Diagram Representation of A Typical Op-Amp	261
12.3 Schematic Symbol	262
12.4 Operational Amplifier Characteristics.....	262
12.5 DC Characteristics	262
12.6 AC Characteristics	264
12.7 Characteristics of Ideal Op-Amp.....	267
12.8 Equivalent Circuit of an Op-Amp.....	268
12.9 Ideal Voltage Transfer Curve.....	268
12.10 Inverting Amplifier.....	269
12.11 Summing Amplifier	274
12.12 Non-inverting Amplifier.....	276
12.13 Voltage Follower	277
12.14 Current-to-Voltage Converter.....	278
12.15 Voltage-to-Current Converter.....	279
12.16 Differential Amplifier.....	279
12.17 Integrator and Differentiator.....	283
12.18 Instrumentation Amplifier	285
12.19 Log Amplifier.....	287
12.20 Antilog or Exponential Amplifier.....	289
12.21 Precision Diode	289
12.22 Half-Wave Rectifier.....	290
12.23 Full-Wave Rectifier.....	291
<i>Student Assignments</i>	292

Chapter 13

Signal Generators and Waveform

Shaping Circuits.....296

13.1 Introduction	296
13.2 Oscillators.....	296
13.3 The Phase-Shift Oscillator	298
13.4 Wien Bridge Oscillator	301
13.5 Colpitts Oscillator	303
13.6 Hartley Oscillator.....	306
13.7 Crystal Oscillators.....	306
13.8 Comparator	309
13.9 Zero-Crossing Detector.....	310
13.10 Sample-And-Hold Circuits.....	311
13.11 Basic Inverting Schmitt Trigger	311
13.12 Schmitt Trigger Oscillator.....	314
13.13 Monostable Multivibrator	316
13.14 The 555 Circuit.....	317
<i>Student Assignments</i>	322

Chapter 14

Filters and Oscillators.....325

14.1 Active Filters.....	325
14.2 Classification of Active Filters	325
14.3 Butterworth Filter.....	327
14.4 Band Pass Filters	332
14.5 Band Stop Filter.....	336
14.6 All Pass Filter	338
14.7 Sallen-Key (VCVS) Filters.....	341
14.8 Voltage-Controlled Oscillators	349
14.9 Mathematical Model of VCOs	351



Semiconductor Physics

1.1 Conductor, Semiconductor and Insulator




Figure-1.1 : Simplified energy band diagrams of (a) insulator (b) semiconductor (c) conductor

1.1.1 Insulators

- An insulating material has an energy band diagram as shown in Fig. 1.1 (a).
- It has a very wide forbidden-energy gap (≈ 6 eV) separating the filled valence band from the vacant conduction band. Because of this, it is practically impossible for an electron in the valence band to jump the gap, reach the conduction band.
- At room temperature, an insulator does not conduct. However, it may conduct if its temperature is very high or if a high voltage is applied across it. This is termed as the **breakdown of the insulator**.
- **Example:** diamond.

1.1.2 Semiconductors

- A semiconductor has an energy-band gap as shown in Fig. 1.1 (b).
- At 0°K semiconductor materials have the same structure as insulators except the difference in the size of the band gap E_G , which is much smaller in semiconductors ($E_G \approx 1$ eV) than in insulators.
- The relatively small band gaps of semiconductors allow for excitation of electrons from the lower (valence) band to the upper (conduction) band by reasonable amount of thermal or optical energy.
- The difference between semiconductors and insulators is that the conductivity of semiconductors can increase greatly by thermal or optical energy.
- **Example:** Ge and Si.

1.1.3 Metals

- There is no forbidden energy gap between the valence and conduction bands. The two bands actually overlap as shown in Fig. 1.1 (c).
- Without supplying any additional energy such as heat or light, a metal already contains a large number of free electrons and that is why it works as a good conductor.
- **Example:** Al, Cu etc.

Remember



Conduction band electrons can move along sea of atoms present in the specimen under consideration while the valence band electrons (restrained electrons) are bound to parent atom. These conduction band electrons are known as **free electrons**.

NOTE



Since the band-gap energy of a crystal is a function of interatomic spacing, it is not surprising that E_G depends somewhat on temperature. It has been determined experimentally that E_G for silicon decrease with temperature at the rate of $3.60 \times 10^{-4} \text{ eV/}^\circ\text{K}$. Hence, for silicon, $E_G(T) = 1.21 - 3.60 \times 10^{-4} T$ and at room temperature (300°K), $E_G = 1.1 \text{ eV}$. Similarly, for germanium, $E_G(T) = 0.785 - 2.23 \times 10^{-4} T$ and at room temperature, $E_G = 0.72 \text{ eV}$.

1.1.4 Semiconductor Materials: Ge, Si and GaAs

Semiconductors: A semiconductor has an energy-band gap as shown in Figure 1.1 (b). At 0°K semiconductor materials have the same structure as insulators except the difference in the size of the band gap E_G , which is much smaller in semiconductors ($E_G \simeq 1 \text{ eV}$) than in insulators.

The relatively small band gaps of semiconductors allow for excitation of electrons from the lower (valence) band to the upper (conduction) band by reasonable amount of thermal or optical energy. The difference between semiconductors and insulators is that the conductivity of semiconductors can increase greatly by thermal or optical energy.

Example: Ge and Si

Semiconductors are a special class of elements having a conductivity between that of a good conductor and that of an insulator.

Single crystal and compound crystal semiconductor are two classifications of semiconductor depending upon number of constitutional elements. Examples of single crystal semiconductors are germanium (Ge) and silicon (Si) whereas compound semiconductors are gallium arsenide (GaAs), cadmium sulphide (CdS), gallium nitride (GaN) and gallium arsenide phosphide (GaAsP) etc.

Intrinsic Materials and Covalent Bonding

Semiconductor in its purest form (without any impurity) is known as **intrinsic semiconductor**.




Figure-1.2 : Covalent bonding of the silicon atom

An intrinsic semiconductor (such as pure Ge or Si), has only four electrons in the outermost orbit of its atoms. When atoms bond together to form molecules of matter, each atom attempts to acquire eight electrons in its outermost shell. This is done by sharing one electron from each of the four neighbouring atoms. This sharing of electrons in semiconductors is known as **covalent bonding**. Figure below shows covalent bonding of the silicon atom.

A covalent bond consists of two electrons, one from each adjacent atom. Both the electrons are shared by the two atoms. At absolute zero, all the valence electrons are tightly bound to the parent atoms. No free electrons are available for electrical conduction. **The semiconductor therefore behaves as a perfect insulator at absolute zero.**

Charge Carriers in Intrinsic Semiconductor

At room temperature (say 300°K) sufficient thermal energy is supplied to make a valence electron of a semiconductor atom to move away from the influence of its nucleus. Thus, a covalent bond is broken. When this happens, the electron becomes free to move in the crystal. This is shown in figure :

When an electron breaks a covalent bond and moves away, a vacancy is created in the broken covalent bond. This vacancy is called a **hole**. Free electrons and holes are always generated in pairs. Therefore, the concentration of free electrons and holes will always be equal in an intrinsic semiconductor

$$n = p = n_i$$

where n_i is called the intrinsic concentration.

Although, strictly speaking, a hole is not a particle; for all practical purposes we can view it as a positively charged particle capable of conducting current. This concept of a hole as a positively charged particle merely helps in simplifying the explanation of current flow in semiconductors.

Effect of Temperature on Conductivity of Intrinsic Semiconductor

A semiconductor (Ge or Si) at absolute zero, behaves as a perfect insulator. At room temperature, some electron-hole pairs are generated. Now, if we raise the temperature further, more electron hole pairs are generated. The higher the temperature, the higher is the concentration of charge carriers. As more charge carriers are made available, the conductivity of intrinsic semiconductor increases with temperature. In other words, the resistivity (inverse of conductivity) decreases as the temperature increases. That is; **semiconductor have negative temperature coefficient of resistance.**

Intrinsic concentration,

$$n_i^2 = A_0 T^3 e^{-\left(\frac{E_{G0}}{kT}\right)}$$

E_{G0} : Energy gap at 0°K in eVs

k : Boltzman's constant in eV/°K

A_0 : Material constant independent of temperature

Extrinsic Materials

In addition to the intrinsic carriers generated thermally, it is possible to create carriers in semiconductors by purposely introducing impurities into the crystal. This process, called **doping**, is the most common technique




Figure-1.3 : (a) Crystal structure (b) Energy band diagram

for varying the conductivity of semiconductors. By doping, a crystal can be altered so that it has a predominance of either electrons or holes. Thus there are two types of doped semiconductors, n-type (majority carriers electrons) and p-type (majority carries holes). When a crystal is doped such that the equilibrium carrier concentrations n_0 and p_0 are different from the intrinsic carrier concentration n_i the material is said to be **extrinsic**.

n-type semiconductor

An n-type semiconductor is created by introducing impurity elements that have five valence electrons (pentavalent), such as antimony, arsenic and phosphorus. The effect of such impurity elements is indicated in figure (1.4). Note that the four covalent bonds are still present. There is, however an additional fifth electron due to the impurity atom, which is unassociated with any particular covalent bond. This remaining electron loosely bound to its parent atom (antimony) atom, is relatively free to move within the newly formed n-type material. Since the inserted impurity atom has donated a relatively “free” electron to the structure;




Figure-1.4 :Antimony impurity in n-type material

Diffused impurities with five valence electrons are called donor atoms.

When impurities or lattice defects are introduced into an otherwise perfect crystal, additional levels are created in the energy band structure, usually within the band gap. For example, an impurity from column V of the periodic table (P, As and Sb) introduces an energy level very near the conduction band in Ge or Si. Such an impurity level is called a donor level. In case of germanium, the distance of new discrete allowable energy level is only 0.01 eV (0.05 eV in silicon) below the conduction band, and therefore at room temperature almost all the “fifth” electrons of the donor material are raised into the conduction band.




Figure-1.5 :Energy-band diagram of n-type semiconductor

NOTE



n-type material is as a whole electrically neutral since ideally the number of positively charged protons in the nuclei is still equal to the number of free and orbiting negatively charged electrons in the structure.

p-type semiconductor

The p-type semiconductor is formed by doping a pure germanium or silicon crystal with impurity atoms having three valence electrons. The elements most frequently used for this purpose are boron, gallium and indium.

Note that, there is now an insufficient number of electrons to complete the covalent bonds of the newly formed lattice. The resulting vacancy is called a hole and is represented by a small circle or a plus sign, indicating the absence of a negative charge. Since the resulting vacancy will readily accept a free electron;

The diffused impurities with three valence electrons are called acceptor atoms.

The resulting p-type material is electrically neutral for the same reasons described for the n-type material.

Atoms from Column-III (B, Al, Ga and In) introduce impurity levels in Ge or Si near the valence band. These levels are empty of electrons at 0K. At low temperatures, enough thermal energy is available to excite electrons from the valence band into the impurity level, leaving behind holes in the valence band. Since this type of impurity level **“accepts”** electrons from the valence band, it is called an acceptor level.




Figure-1.6 : Boron impurity in p-type material




Figure-1.7 : Energy-band diagram of p-type semiconductor

Standard Doping Levels

1. Moderate doping : 1 in $(10^6 - 10^8)$: P, N
 2. Lightly doped : 1 in 10^{11} : P^-, N^-
 3. Highly (heavily) doped : 1 in 10^3 : P^+, N^+
- ⇒ 1 : 10^6 or 1 in 10^6 or $1/10^6$ is read as “1 impurity atom in 10^6 atoms”.

1.2 The Mass-action Law

In a semiconductor under thermal equilibrium (constant temperature) the product of electrons and holes concentrations is always a constant and is equal to the square of intrinsic carrier concentration.

$$np = n_i^2$$

The intrinsic concentration n_i is a function of temperature.

The law is mainly used to calculate the concentration of minority carriers. In n-type semiconductor, the electrons are called the majority carriers, and the holes are called the minority carriers. In a p-type material, the holes are the majority carriers, and the electrons are the minority carriers.

For a p-type semiconductor,

$$p_n = \frac{n_i^2}{n_n}$$

For an n-type semiconductor,

$$n_n = \frac{n_i^2}{p_n}$$

or, Minority carrier concentration = $\frac{n_i^2}{\text{Majority carrier concentration}}$

but, Majority carrier concentration \propto Doping concentration

so, Minority carrier concentration $\propto \frac{1}{\text{Doping concentration}}$

or, $\boxed{\text{Minority carrier concentration} \times \text{Doping concentration} = n_i^2}$

In a semiconductor, if majority carrier concentration increases the minority carrier concentration decreases this is due to the recombinations.

Example 1.1

Why silicon and germanium are generally preferred compare to GaAs?

Solution:

At, 0 K

	Ge	Si	GaAs
E_g	0.785 eV	1.21 eV	1.58 eV

As the energy gap between valence band and conduction band of GaAs is more than Ge and Si, so these are good semiconductor.

Example 1.2

Explain GaAs is used in C-MOS technology.

Solution:

From power dissipation (P_D) point of view,


Ge can withstand upto 100°C

Si can withstand upto 200°C

GaAs can withstand greater than 2000°C

and mobility of electron, point of view,

$$\begin{aligned}\mu_e(\text{Si}) &= 1300 \text{ cm}^2/\text{V-sec} \\ \mu_e(\text{Ge}) &= 3800 \text{ cm}^2/\text{V-sec} \\ \mu_e(\text{GaAs}) &= 8500 \text{ cm}^2/\text{V-sec}\end{aligned}$$



Example 1.3 What is the importance of *Si* compared to *Ge*?

Solution:

1. $\left. \begin{array}{l} Si \rightarrow I_0 \text{ in nano-ampere} \\ Ge \rightarrow I_0 \text{ in micro-ampere} \end{array} \right\} \text{Because of gap difference}$

I_0 ideally should be zero but practically, it should be less in value.

2. Temperature withstand capacity

$$Ge \rightarrow 100^\circ\text{C}$$


$$Si \rightarrow 200^\circ\text{C}$$

3. Peak inverse voltage (PIV) rating. It is the maximum reverse biased voltage at which the diode can withstand.

$$Ge \rightarrow 400 \text{ V}$$

$$Si \rightarrow 1000 \text{ V}$$

4. Silicon is cheap compared to germanium.



NOTE: Drawback of *Si* is less conductivity due to more energy gap.

1.3 Charge Neutrality Equation

Any part of a semiconductor bar is always electrically neutral.

or

Total positive charge densities = Total negative charge densities.

$$P + N_D = n + N_A$$

***n*-type**

$$P + N_D = n + N_A$$

$$n > p ; N_A \approx 0 \text{ (} n\text{-type)}$$

$$\Rightarrow \frac{n_i^2}{n} + N_D = n \Rightarrow n^2 - N_D n - n_i^2 = 0$$

$$\Rightarrow n = \frac{N_D}{2} \pm \sqrt{\left(\frac{N_D}{2}\right)^2 + n_i^2} = \frac{N_D}{2} + \sqrt{\left(\frac{N_D}{2}\right)^2 + n_i^2} \quad (n > 0, \text{ so only +ve sign})$$

$$n = \frac{N_D}{2} + \sqrt{\left(\frac{N_D}{2}\right)^2 + n_i^2}$$

$$N_D \gg n_i$$

So,

$$n \approx N_D$$

Similarly, for ***p*-type**

$$p = \frac{N_A}{2} + \sqrt{\left(\frac{N_A}{2}\right)^2 + n_i^2}$$

$$N_A \gg n_i$$

$$p \approx N_A$$

1.4 Drift Current

It occurs in metals and semiconductor.

$$V \propto E$$

$$V = \mu E$$

$V \rightarrow$ drift velocity


$E \rightarrow$ Electric field

$\mu \rightarrow$ proportionality constant (mobility)

Mobility (μ)

$$\mu = \frac{V}{E} = \frac{\text{Drift velocity}}{\text{electric field}} \frac{m^2}{V \text{ sec.}}$$

Effect of Electric Field on Mobility



$\mu = \text{constant}$	$E < 10^3 \text{ V/cm}$
$\mu \propto \frac{1}{\sqrt{E}}$	$10^3 < E < 10^4 \text{ V/cm}$
$\mu \propto \frac{1}{E}$	$E > 10^4 \text{ V/cm}$

1.5 Current Density (J)

$$J = \frac{I}{A}$$

$$I = \frac{N \times e}{t} = \frac{\text{total charge}}{\text{time}}$$

$$J = \frac{N \times e}{t \times A} = \frac{N \times e}{\frac{L}{V} \times A} \quad \left[t = \frac{L}{V} \right]$$

$$J = \frac{N \times e}{L \times A} \times V$$

$$J = neV$$

$n \rightarrow$ number of electron per unit volume

$$J = \rho V$$

$\rho = ne =$ charge density
 $=$ charge per unit volume

For metal:

$$J = neV$$

$$V = \mu E$$

$$J = ne\mu E$$

$$J = \rho\mu E \quad (\rho = ne)$$

$$\sigma = \rho\mu \Rightarrow J = \sigma E$$

($\sigma =$ conductivity)

Semi conductor:

$$J_{sc} = J_n + J_p$$

$$J_n = n \times q \times \mu_n \times E$$

$$J_p = n \times q \times \mu_p \times E$$

$$J_{sc} = (n\mu_n + p\mu_p) qE$$

and we know,

$$J = \sigma E$$

So,

$$\sigma = (n\mu_n + p\mu_p)q$$

Case-I: Intrinsic semiconductor

$$n = p = n_i$$

$$\sigma_{intrinsic} = n_i(\mu_n + \mu_p)q$$

Case-II: extrinsic semiconductor

$$n \gg p \text{ (for } n\text{-type)}$$

$$\sigma_{n\text{-type}} \simeq n\mu_n q$$

or,

$$\sigma_{n\text{-type}} \simeq N_D \mu_n q$$

and for p -type,

$$\sigma_{p\text{-type}} \simeq p\mu_p q$$

$$\sigma_{p\text{-type}} \simeq N_A \mu_p q$$

Example 1.4

Pure silicon has an electrical resistivity of 3000 Wm. If the free carrier density in it is $1.1 \times 10^6 \text{ m}^{-3}$ and the electron mobility is three times that of hole mobility, calculate the mobility values of electrons and holes.

Solution:

Conductivity,

$$(\sigma) = \frac{1}{\text{resistivity}}$$

For a pure silicon,

$$\sigma = (\mu_n + \mu_p) n_i e$$

Where,

$$\mu_n = \text{electron mobility}$$

$$\mu_p = \text{hole mobility}$$

$$n_i = \text{carrier concentration}$$

$$e = \text{electron charge} \approx 1.6 \times 10^{-19} \text{C}$$

Given that,

$$\mu_n = 3\mu_p$$

So,

$$\frac{1}{3000} = (3\mu_p + \mu_p) \times 1.1 \times 10^6 \times 1.6 \times 10^{-19}$$

or

$$\mu_p = 4.7348 \times 10^8 \text{ m}^2/\text{V-sec}$$

and

$$\mu_n = 3\mu_p = 3 \times 4.7348 \times 10^8 = 1.42 \times 10^9 \text{ m}^2/\text{V-sec}$$

Example 1.5

The intrinsic resistivity of Germanium at room temperature is 0.47 $\Omega\text{-cm}$. The electron and hole mobilities at room temperature are 0.39 and 0.19 $\text{m}^2/\text{V-s}$ respectively. Calculate the density of electrons in the intrinsic semiconductor. Also calculate the drift velocities of these charge carriers for a field of 10 kV/m.

Solution:

Given that,

Resistivity,

$$\rho_i = 0.47 \, \Omega \text{ cm}$$

$$\mu_n = 0.39 \text{ m}^2/\text{V-sec}$$

$$\mu_p = 0.19 \text{ m}^2/\text{V-sec}$$

Now,

$$\rho_i = \frac{1}{\sigma_i} = \frac{1}{n_i q (\mu_n + \mu_p)}$$

$$0.47 \times 10^{-2} = \frac{1}{n_i \times 1.6 \times 10^{-19} (0.39 + 0.19)}$$

$$n_i = 2.29 \times 10^{21} / \text{m}^3$$

Drift velocity,

$$v_d = \mu E$$

For electron:

$$v_d = \mu_n E = 0.39 \times 10 = 3.9 \text{ km/sec}$$

For hole:

$$v_d = \mu_p E = 0.19 \times 10 = 1.9 \text{ km/sec}$$

Example 1.6

Define carrier mobility. Draw a graph showing the variation of carrier mobility in a semiconductor with increasing temperature. A 100-ohm resistor is to be made at room temperature in a rectangular silicon bar of 1 cm in length and 1 mm² in cross-sectional area by doping it appropriately with phosphorous atoms. If the electron mobility in silicon at room temperature be 1350 cm²/V.sec, calculate the dopant density needed to achieve this. Neglect the insignificant contribution by the intrinsic carriers.

Solution:

If a constant electric field E is applied to the semi conductor, as a result of this electrostatic force and electron would be accelerated and velocity would increase indefinitely with time, till it will not collide with ions. At each in elastic collision with an ion, electron loss energy and steady state condition is reached, where finite value of speed called drift speed is attained.

So, drift speed v_d is proportional to ϵ .

$$v_d \propto E$$

$$v_d = \mu E$$

where,

 μ = Mobility

Mobility is defined as drift velocity per unit electric field.


$$\mu = \frac{v_d}{E}$$

Relation between Mobility with Temperature

Two types of scattering influence electron and hole mobility are:

1. Lattice scattering
2. Impurity scattering

In Lattice scattering a carrier moving through crystal is scattered by a vibration of lattice, resulting from Temperature. Frequency of such scattering events increases as temperature increases, since thermal agitation of lattice becomes greater. Therefore, we should expect the mobility to decrease with increase in temperature. On other hand moving scattering from crystal defect becomes dominant mechanism at low temperature since a slowly moving carrier is likely to be scattered more strongly by an interaction with a charged ion than is a carrier with greater momentum. So impurity scattering event cause a decrease in mobility with decrease in temperature.



$$\begin{aligned} R &= 100 \, \Omega \\ l &= 1 \, \text{cm} \quad \mu_n = 1350 \, \text{cm}^2/\text{vsec} \\ A &= 1 \, \text{mm}^2 = 10^{-2} \, \text{cm}^2 \end{aligned}$$

we know that,

$$R = \rho \frac{l}{A}$$

$$\rho = \frac{RA}{l} = \frac{100 \times 10^{-2}}{1} = 1 \, \Omega\text{cm}$$

$$\sigma_N = \frac{1}{\rho} = nq\mu_n$$

$$n = \frac{1}{\rho \times q \times \mu_n} = \frac{1}{1 \times 1.6 \times 10^{-19} \times 1350} = 4.6 \times 10^{15}/\text{cm}^3$$

For N-type:

$$\begin{aligned} n &\simeq N_D \\ N_D &= 4.6 \times 10^{15}/\text{cm}^3 \end{aligned}$$

Example 1.7

What fraction of drift current is due to electrons in intrinsic "Ge"?

Solution:

$$\begin{aligned} I_{\text{drift}} &= I_n + I_p \\ &= (nq\mu_n) \times E \times A + pq\mu_p \times E \times A \end{aligned}$$

$$\% \text{ fraction of electron current} = \frac{I_n}{I_n + I_p} = \frac{nq\mu_n EA}{(nq\mu_n EA) + (pq\mu_p EA)}$$

Since, intrinsic, $n = p = n_i$

$$\% \text{ fraction} = \frac{\mu_n}{\mu_n + \mu_p} = \frac{3800}{3800 + 1800}$$


$$= 0.68 \text{ or } 68\% \text{ (for Ge)}$$

$$\% \text{ hole current} = 1 - 0.68 = 0.32 \text{ or } 32\%$$

1.6 Diffusion Current

It occurs in a non-uniformly doped semiconductor,

- Rate of change of concentration with respect to distance x is called as diffusion current. It is also called concentration gradient $\frac{dn}{dx}$.
- Without electric field, there is movement of charge from high density to low density side, and this movement is called diffusion current.
i.e. $I_{\text{diff}} \neq 0$
- Best examples of non-uniformly doped SC will be P-N junction.



Non-uniformly doped semiconductor

**Student's
Assignments**

- Q.1** A semiconductor is irradiated with light such that carriers are uniformly generated throughout its volume. The semiconductor is n-type with $N_D = 10^{19}/\text{cm}^3$. If the excess electron concentration in the steady state is $\Delta n = 10^{15}/\text{cm}^3$ and if $\tau_p = 10 \mu\text{sec}$. (minority carries life time) the generation rate due to irradiation
- is 10^{20} e-h pairs/ cm^3/s
 - is 10^{24} e-h pairs/ cm^3/s
 - is 10^{10} e-h pairs/ cm^3/s
 - cannot be determined, the given data is insufficient
- Q.2** In a p-type Si sample the hole concentration is $2.25 \times 10^{15}/\text{cm}^3$. The intrinsic carrier concentration is $1.5 \times 10^{10}/\text{cm}^3$ the electron concentration is
- zero
 - $10^{10}/\text{cm}^3$
 - $10^5/\text{cm}^3$
 - $1.5 \times 10^{25}/\text{cm}^3$
- Q.3** A Silicon sample A is doped with 10^{18} atoms/ cm^3 of Boron. Another sample B of identical dimensions is doped with 10^{18} atoms/ cm^3 of Phosphorus. The ratio of electron to hole mobility is 3. The ratio of conductivity of the sample A to B is
- 3
 - 1/3
 - 2/3
 - 3/2
- Q.4** The concentration of minority carriers in an extrinsic semiconductor under equilibrium is
- directly proportional to the doping concentration
 - inversely proportional to the doping concentration
 - directly proportional to the intrinsic concentration
 - inversely proportional to the intrinsic concentration
- Q.5** Under low level injection assumption, the injected minority carrier current for an extrinsic semiconductor is essentially the
- diffusion current
 - drift current
 - recombination current
 - induced current
- Q.6** A heavily doped n-typed semiconductor has the following data:
Hole-electron mobility ratio : 0.4
Doping concentration : 4.2×10^8 atoms/ m^3
Intrinsic concentration : 1.5×10^4 atoms/ m^3
The ratio of conductance of the n-type semiconductor to that of the intrinsic semiconductor of same material and at the same temperature is given by
- 0.00005
 - 2,000
 - 10,000
 - 20,000
- Q.7** The electron and hole concentrations in an intrinsic semiconductor are n_i per cm^3 at 300 K. Now, if acceptor impurities are introduced with a concentration of N_A per cm^3 (where $N_A \gg n_i$) the electron concentration per cm^3 at 300 K will be
- n_i
 - $n_i + N_A$
 - $N_A - n_i$
 - $\frac{n_i^2}{N_A}$
- Q.8** The ratio of the mobility to the diffusion coefficient in a semiconductor has the unit
- V^{-1}
 - $\text{cm} \times \text{V}^{-1}$
 - $\text{V} \times \text{cm}^{-1}$
 - $\text{V} \times \text{s}$
- Q.9** Drift current in semiconductors depends upon
- only the electric field
 - only the carrier concentration gradient
 - both the electric field and the carrier concentration
 - both the electric field and the carrier concentration gradient

■ ANSWERS

1. (a) 2. (c) 3. (b) 4. (b) 5. (a)
6. (d) 7. (d) 8. (a) 9. (c)



**Student's
Assignments**

Explanations

1. (a)

10^{20} e-h pairs/cm³/s

Given that, $\Delta n = 10^{15}/\text{cm}^3$

$$\tau_p = 10 \mu\text{sec} = 10 \times 10^{-6} \text{ sec.}$$

$$\text{Generation rate} = \frac{\Delta n}{\tau_p} = \frac{10^{15}}{10 \times 10^{-6}}$$

$$= 10^{20} \text{ e-h pairs/cm}^3/\text{s}$$

2. (c)

By Mass Action Law

$$n \cdot p = n_i^2$$

where,

n = electron concentration

p = hole concentration

n_i = intrinsic carrier concentration

$$p = 2.25 \times 10^{15}/\text{cm}^3$$

$$n_i = 1.5 \times 10^{10}/\text{cm}^3$$

$$n = \frac{n_i^2}{p} = \frac{(1.5 \times 10^{10})^2}{2.25 \times 10^{15}} = \frac{2.25 \times 10^{20}}{2.25 \times 10^{15}}$$

$$n = 10^5/\text{cm}^3$$

3. (b)

$$\sigma_n = nq\mu_n$$

$$\frac{\sigma_p}{\sigma_n} = \frac{\mu_p}{\mu_n} = \frac{1}{3}$$

4. (b)

$$np = n_i^2$$

n_i = constant

For n-type p is minority carrier concentration

$$p = \frac{n_i^2}{n}$$

$$p \propto \frac{1}{n}$$

6. (d)

For n-type semiconductor, $\sigma_n = nq\mu_n$

For intrinsic semiconductor,

$$\sigma_i = n_i q (\mu_n + \mu_p)$$

$$\frac{\sigma_n}{\sigma_i} = \frac{n\mu_n}{n_i(\mu_n + \mu_p)}$$

$$= \frac{4.2 \times 10^8 \times \mu_n}{1.5 \times 10^4 \times \mu_n \left(1 + \frac{\mu_p}{\mu_n}\right)}$$

$$= \frac{4.2 \times 10^8}{1.5 \times 10^4 \times 1.4} = 2 \times 10^4$$

7. (d)

By the law of electrical neutrality

$$p + N_D = n + N_A$$

as $N_D = 0$

$$N_A \gg n_i \approx 0 \quad p = N_A$$

using mass action law $np = n_i^2$

$$\text{So,} \quad n = \frac{n_i^2}{p} = \frac{n_i^2}{N_A}$$

8. (a)

$$\frac{D}{\mu} = V_T$$

$$\Rightarrow \frac{\mu}{D} = \frac{1}{V_T} \Rightarrow \text{units : } V^{-1}$$

9. (c)

$$J = n e v_d$$

Put, $v_d = \mu E$

$$\therefore J = n e \mu E$$

Hence, $I = n e \mu EA$

So, I depends upon carrier concentration and electric field.

■■■■